

Product : SuperLite XLT® **Grade :** SLXLTA.0641BZ

Status⁷ : Commercial

Revision : 1

Date : 20-Dec-2007

General Description

AZDEL SuperLite SLXLTA.0651BZ is a thermoformable, thermoplastic composite sheet comprised of a low-density polypropylene and chopped glass-fiber core, combined with a PET scrim with barrier film attached to one surface and a perforated adhesive film to the other surface. This material is typically used as a substrate in semi-structural applications where a very high strength-to-weight ratio is required, such as in automotive headliners, door panels, rear parcel shelves, sunshades and other interior trim.

Construction Code	Surface A	Surface B
BZ	Perforated adhesive film	Spunbond PET scrim with Barrier film

Typical Properties¹ - Independent of Molded Thickness

Property	Test Method	Unit	Target Value
Basis Weight (mass-per-unit-area)			
- Low density Core	ASTM D-3776	g/m ²	640
- Total (including film and scrim)	ASTM D-3776	g/m ²	750
Sheet Thickness (as produced)		mm	
Free-Loft ratio ² (maximum, when heated to 205°C)	Internal		5.5:1
Color			
- Low Density Core	Visual		Natural
- PET Scrim with Barrier film	Visual		White
- Adhesive Film	Visual		Clear
Flammability			
- Maximum Burn Rate	FMVSS-302	mm/min.	35
- Self-extinguishing?			No
Fogging (Haze) - Minimum Fog Number			
Odor - Maximum Number (using 1-Liter Glass Jars)			
Maximum in-use operating temperature ³		°C	90

Typical Properties¹ - Dependent on Molded Thickness

Property	Test Method	Unit	Molded Thickness (mm)		
			4.0	5.0	6.5
Specific Gravity					
MD ⁴ Flex. Slope	AZDEL Internal	N/cm	32.90	45.90	47.70
TD ⁵ Flex. Slope	AZDEL Internal	N/cm	23.00	25.80	32.40
MD Flex. Peak Load	AZDEL Internal	N	11.40	13.00	12.00
TD Flex. Peak Load	AZDEL Internal	N	8.40	9.30	9.00
Average Flex. Peak Load	AZDEL Internal	N	9.90	11.15	10.50
MD/TD Peak Load Ratio	AZDEL Internal		1.36	1.40	1.33
Toughness					

Product : SuperLite XLT® **Grade :** SLXLTA.0641BZ

Status⁷ : Commercial

Revision : 1

Date : 20-Dec-2007

Typical Properties¹ - Dependent on Molded Thickness (cont'd)

Property	Test Method	Unit	Molded Thickness (mm)				
			4.0	5.0	6.5		
Dynatup Impact	ASTM C-522	cfm	none	none	none		
Air Permeability							
Acoustics (with Fabric ⁶)	SAE J1400	@ 500 Hz			0.08		
- Sound Absorption Coef.							
- Sound Absorption Coef.						@ 1000 Hz	0.19
- Sound Absorption Coef.						@ 2000 Hz	0.44
- Sound Absorption Coef.	SAE J1400	@ 4000 Hz	0.93				
Peel Test							
- Surface A							
- Surface B							

Notes

1. Measured on flat plaques.
2. The free-loft ratio is the ratio of original, as produced, sheet thickness versus the lofted sheet thickness when heated to 205°C and not molded.
3. The maximum in-use temperature is typically driven by the adhesion of surface skins to the low density core, or by the de-bonding temperature of the adhesive film.
4. MD = Properties measured in the as manufactured Machine Direction.
5. TD = Properties measured perpendicular to the as manufactured Machine Direction (i.e.; Transverse.)
6. A typical automotive fabric and foam are used for the acoustical evaluation. Please contact your AZDEL representative if you want your own cover-stock tested with this product.
7. This Product is commercially available, subject to AZDEL's Standard Terms of Sale.

AZDEL, Inc.

300 Enterprise Drive, Suite A, Forest, VA 24551, USA

Tel: (800) 635-7021 • Fax: (434) 455-2785 • Email: sales@azdel.com • www.azdel.com

In as much as AZDEL has no control over the use to which others may put our material, it does not guarantee that the same results as those described herein will be obtained. Nor does AZDEL guarantee the effectiveness of safety of any possible or suggested design for articles of manufacture as illustrated. Each user of the material or design or both should make his/her own tests to determine the suitability of the material or any material for the design, as well as the suitability of the material or design or both for his/her own particular use. Statements concerning possible or suggested use of the materials or design are not to be construed as constituting a license under an AZDEL patent covering such use or as recommendations for use of such materials or designs in the infringement of any patent.